



Thermoplastic Modified Epoxy Resin

SP-TMEP70ASP is a dissolution product that consists of 70% thermoplastic-modified epoxy resin dissolved in 30% Bisphenol A-based liquid epoxy resin.

The benefits from the use of thermoplastic modified epoxy resins include (but are not limited to) improvements in fracture toughness, peel strength, and strain to failure. Unlike rubber-modified epoxy materials, these thermoplastic-modified epoxy resins help with the aforementioned properties without sacrificing glass transition temperature and adhesion.

Commercially available modified thermoplastic epoxy resins have had limited use due to their high softening point, making them difficult to incorporate into various products (such as adhesives, coatings and preregs). Now, a series of thermoplastic-modified epoxy resins are available with a range of softening points to balance the ease of incorporation with the performance of the end product.

These thermoplastic modified epoxy resins may be cured using conventional curing technologies for single component systems (e.g. with dicyandiamide).

Specific Physical Form:	Solid Flake or Granule
Color:	Amber to Brown
Shelf Life:	3 Years

Typical Properties:

Specific Gravity:	1.20 g/cc
Epoxy Equivalent Weight:	550 - 660 g/eq.
Viscosity at 248°F (120°C):	10,000 - 40,000 Poise
Hydroxyl Equivalent Weight of Polymeric Portion	390 - 400 g/eq.
Molecular Weight of Polymeric Portion	Mn = 6,000 - 12,000 g/mol Mw = 25,000 - 35,000 g/mol

Disclaimer:

The information provided above is believed to be accurate and represents the best information available at the time. Persons using the information must make their own determinations and assessments as to the suitability of the relevant information for their purposes. Springfield Industries assumes no liability arising out of the use of or reliance on this information, or out of the use or the performance of the product.